

(19) 日本国特許庁 (J P)

## (12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平9-169753

(43) 公開日 平成9年(1997)6月30日

(51) Int.Cl. <sup>6</sup>	識別記号	庁内整理番号	F I	技術表示箇所
C 0 7 D 305/12			C 0 7 D 305/12	
B 0 1 J 31/12			B 0 1 J 31/12	X
31/22			31/22	X
// C 0 7 B 61/00	3 0 0		C 0 7 B 61/00	3 0 0

審査請求 未請求 請求項の数 1 O L (全 4 頁)

(21) 出願番号	特願平7-332967	(71) 出願人	000003182 株式会社トクヤマ 山口県徳山市御影町1番1号
(22) 出願日	平成7年(1995)12月21日	(72) 発明者	服部 憲和 山口県徳山市御影町1番1号 株式会社トクヤマ内
		(72) 発明者	西田 治男 山口県徳山市御影町1番1号 株式会社トクヤマ内

(54) 【発明の名称】 2-オキセタノン類化合物の製造方法

(57) 【要約】

【課題】 2-オキセタノン類化合物を安定的に高選択率で単離して得る方法を提供する。

【解決手段】 エチレンオキサイド等のオキシラン化合物と一酸化炭素を混合したものを、ジコバルトオクタカルボニル等のコバルト化合物を用いて調製したコバルト系触媒に流通下接触させて反応させ、2-オキセタノン等の2-オキセタノン類化合物を高選択率で得る2-オキセタノン類化合物の製造方法。

**THIS PAGE BLANK (USPTO)**

【特許請求の範囲】

【請求項1】 オキシラン化合物と一酸化炭素とをコバルト系触媒に流通下接触させて反応させることを特徴とする2-オキセタノン類化合物の製造方法。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】本発明は、コバルト系触媒を用いた流通式反応による2-オキセタノン類の製造方法に関する。

【0002】

【従来の技術】最もよく知られている2-オキセタノン類化合物の製造方法は、ケテン類とアルデヒド類をフリーデル・クラフツ系触媒の存在下に反応させるものである。しかし、ケテン類及びアルデヒド類自体が純度の高いものを得ることが困難な場合が多く、しかも共に反応性が高いために、得られた2-オキセタノン類化合物中には多量且つ多種類の副生成物が混入するという問題があった。副生成物としては、酢酸、アクリル酸、3-ヒドロキシプロピオン酸等のカルボン酸類及びそれらの酸無水物が主であり、これらは2-オキセタノン類化合物を重合する場合に、著しい重合阻害作用を示す。

【0003】英国特許1020575号公報には、エチレンオキサイドと一酸化炭素を、ジコバルトオクタカルボニル触媒存在下に、100度、100～300気圧でバッチ式反応を行うことにより、主成分として2-オキセタノンのオリゴマーを得ており、この生成物中に2-オキセタノンも存在していることが述べられている。

【0004】また、特開平6-65223号公報には、コバルト源とヒドロキシ置換ピリジン化合物とからなる触媒系を用いて、バッチ式反応でオキシラン化合物を一酸化炭素によってカルボニル化する事により、高収率で

2-オキセタノン類化合物を得る技術が示されている。しかし、使用した触媒系中のヒドロキシ置換ピリジン化合物が、生成した2-オキセタノン類化合物の重合開始剤として作用するため、生成した2-オキセタノン類化合物は、生成とともに即座に重合してしまうことが明細書に明記されている。従ってこの触媒系において均一系液相バッチ式反応で行う限り、2-オキセタノン類化合物を重合する前に単離する事は不可能である。

【0005】

【発明が解決しようとする課題】本発明は、2-オキセタノン類化合物を、副生成物をほとんど含まない状態で、選択的に単離し得る製造方法を提供するものである。


【0006】

【課題を解決するための手段】本発明者らは、鋭意研究を重ねた結果、流通法を採用し、触媒との接触時間を短くすると、2-オキセタノン類化合物を副生成物をほとんど含まない状態で単離し得ることを見だし、本発明を完成するに至った。即ち、本発明は、オキシラン化合物と一酸化炭素とをコバルト系触媒に流通下接触させて反応させることを特徴とする2-オキセタノン類化合物の製造方法である。

【0007】本発明は、流通下に下記式で示される接触反応を行わせることを特徴としている。こうすることにより、触媒活性点上で生成した2-オキセタノン類化合物を速やかに触媒層から脱離することができ、その結果として2-オキセタノン類化合物を単離することができる。また、副反応も抑えられるため、得られる2-オキセタノン類化合物中に不純物は極めて少なくなる。

【0008】

【化1】



【0009】

【発明の実施の形態】本発明におけるオキシラン化合物とは、その構造中に三員環エーテル構造を少なくとも1個含有する化合物であれば、特に制限されない。好ましく使用されるオキシラン化合物を例示するならば、エチレンオキサイド、プロピレンオキサイド、イソブテンオキサイド、2-ブテンオキサイド、スチレンオキサイド、1, 2-エポキシヘキサン、1, 2-エポキシオクタン、シクロヘキセンオキサイド、グリシジルメチルエーテル、グリシジルメタクリレート、及びエピクロルヒドリン等が挙げられる。これらの中でも反応性が特に優れているものとして、エチレンオキサイド、プロピレンオキサイド及びスチレンオキサイドがより好ましく用いられる。

【0010】本発明におけるコバルト系触媒は、コバルトを含有してなる化合物（コバルト源ともいう）を原料として調製された触媒なら特に制限されない。このコバルト源としては、ジコバルトオクタカルボニル、硝酸コバルト、塩化コバルトのような無機化合物、あるいは酢酸コバルトやコバルトのアセチルアセトネート錯体などのような有機金属化合物などが挙げられる。この中でも特に、ジコバルトオクタカルボニル、硝酸コバルト、及び酢酸コバルトなどが好適に用いられる。これらをそのまま触媒として使用することも可能であるが、該コバルト系触媒は流通式反応に使用する触媒なので反応条件下で固体として存在することが好ましく、そのため、通常含浸法などによって、シリカゲル、アルミナ、ゼオライト、シリカアルミナ、ジルコニア、或いは不活性ガラ

**THIS PAGE BLANK (USPTO)**

ス等の何らかの担体上に担持したものが好適である。更にこれらのコバルト源及び担体上に担持したものを、窒素や水素、或いは一酸化炭素等の各種ガス雰囲気下で加熱処理等を施したのも用いられる。なお、コバルト系触媒の調製に当たっては、コバルト源に加えて、反応活性を向上させる助触媒となり得る化合物を混入して使用することもできる。好適に用いられる助触媒としては、ヒドロキシ置換ピリジン系化合物が挙げられる。

【0011】本発明におけるコバルト系触媒上のコバルト濃度は、特に限定されないが、転化率と選択率のバランスを考慮すると、触媒1ml当たり0.01~10mmol原子量であることが好ましく、0.1~5mmol原子量であることがより好ましい。コバルト濃度が触媒1ml当たり0.01mmol原子量未満の場合は、高い転化率を得るためには触媒を多量に充填しなければならず、工業的に不利な場合がある。また、コバルト濃度を触媒1ml当たり10mmol原子量を越えても、コバルトを多量に使用したことによる効果は少ない。

【0012】本発明の製造方法の実施態様については特に限定されないが、一般的な方法を例示すれば次に述べる通りである。即ち、コバルト系触媒を充填した反応管を所定の反応温度に加温し、そこへオキシラン化合物と一酸化炭素を一定比率で混合した原料を所定の流速で供給し、触媒層において反応させる。触媒層を通過した反応混合物から未反応の原料オキシラン化合物及び一酸化炭素を除去することにより、2-オキセタノン類化合物を得る。必要があればその後2-オキセタノン類化合物を蒸留精製しても良い。

【0013】本発明の製造方法において、オキシラン化合物は一酸化炭素と混合され、原料混合体として触媒層へと供給される。オキシラン化合物と一酸化炭素はモル比1:1で反応し、2-オキセタノン類化合物を生成するが、原料混合体中での混合比は、必ずしも1:1にする必要はなく、一酸化炭素を過剰にした方が収率は向上する。好ましい混合比はオキシラン化合物に対して一酸化炭素が1~50倍、より好適には1~20倍である。1倍を下回る場合は転化率及び選択率が低くなり、50倍を越える場合はオキシラン化合物が希釈され過ぎるために転化率は下がる傾向がある。なお、触媒層通過後に、過剰分の一酸化炭素及び未反応のオキシラン化合物は、生成物と分離し、必要ならば精製し、再度反応原料として使用することができる。

【0014】本発明の製造方法において、反応原料と触媒の接触時間は特に限定されないが、転化率と選択率のバランスを考慮すると、0.01~30秒の範囲が好適である。更に接触時間が0.1~10秒の範囲の場合には、高転化率と高選択率が同時に実現され、特に好適である。ここで接触時間とは、原料が触媒層の中を通過するために要する時間である。例えば触媒層がXmlの容積であり、原料混合物が毎秒Ymlの流速で供給されている場合、接

触時間はX/Y秒と表される値である。この接触時間は、転化率と選択率に影響する重要な要素であり、原料混合体の供給速度、触媒のコバルト濃度、及び触媒使用量によって制御することができる。

【0015】本発明における接触反応は比較的穏やかな条件で進行させることが好ましい。反応温度は特に限定されないが、転化率と選択率のバランスから20~120度が好ましく、40~80度がより好ましい。反応圧は大気圧~50気圧が好ましく、大気圧~30気圧がより好ましい。50気圧を越える場合は、装置の構造上、コスト的に不利になる場合がある。

【0016】

【発明の効果】2-オキセタノン類化合物は極めて反応性に富むため、様々な薬品類の原料や、ポリマーの単量体として有用である。特に2-オキセタノンは生分解性プラスチックであるポリプロピオラクトンの原料単量体として非常に重要である。

【0017】本発明によって、2-オキセタノン類化合物を、安定的に高選択率で単離することができる。

【0018】

【実施例】本発明を、実施例により、さらに詳細に説明するが、本発明はこれらの実施例に限定されるものではない。

【0019】実施例1

ジコバルトオクタカルボニル1gを粒径0.8mm、表面積0.65cm<sup>2</sup>/gの不活性ガラス粒子7g(5ml)に担持したもの

(コバルト濃度1.2mmol原子量/ml)をステンレス製反応管に充填し、一酸化炭素10気圧雰囲気下で100度で2時間処理することにより、触媒を調製した。ここに、エチレンオキサイドと一酸化炭素を1:10の比率で混合した原料を流通させた。反応温度は60度、反応圧は10気圧、接触時間は1.5秒で行った。得られた生成物は高速液体クロマトグラフィー及びガスクロマトグラフィーによって分析した。その結果、エチレンオキサイドに対する転化率は30%、反応管より出てきた反応混合物は、原料の他は2-オキセタノンのみであり、その他の副生成物は検出されなかった。

【0020】実施例2

ジコバルトオクタカルボニル1gを粒径75~500μm、表面積500m<sup>2</sup>/gのシリカゲル粒子3.5g(6.5ml)に担持したもの(コバルト濃度0.9mmol原子量/ml)をステンレス製反応管に充填し、一酸化炭素10気圧雰囲気下で100度で2時間処理することにより、触媒を調製した。ここに、プロピレンオキサイドと一酸化炭素を1:10の比率で混合した原料を流通させた。反応温度は60度、反応圧は10気圧、接触時間は0.5秒で行った。得られた生成物は高速液体クロマトグラフィー及びガスクロマトグラフィーによって分析した。その結果、プロピレンオキサイドに対する転化率は25%、反応管より出てきた反応混合物中の4-メチル-2-オキセタノンの選択率は100%であり、そ

**THIS PAGE BLANK (USPTO)**

の他の副生成物は検出されなかった。

### 【0021】実施例3

酢酸コバルト1gを粒径100~300 $\mu$ m、表面積200m<sup>2</sup>/gの活性アルミナ粒子3.5g (5.2ml) に担持したもの (コバルト濃度1.1mmol原子量/ml) をステンレス製反応管に充填し、一酸化炭素10気圧雰囲気下で100度で2時間処理することにより、触媒を調製した。ここに、スチレンオキシドと一酸化炭素を1:10の比率で混合した原料を流通させた。反応温度は60度、反応圧は10気圧、接触時間は8秒で行った。得られた生成物は高速液体クロマトグラフィー及びガスクロマトグラフィーによって分析した。その結果、スチレンオキシドに対する転化率は21%、反応管より出てきた反応混合物中の4-フェニル-2-オキセタノンの選択率は100%であり、その他の副生成物

は検出されなかった。

### 【0022】実施例4~17

ジコバルトオクタカルボニル1gを粒径0.8mm、表面積0.65cm<sup>2</sup>/gの不活性ガラス粒子7g (5ml) に担持したもの (コバルト濃度1.2mmol原子量/ml) をステンレス製反応管に充填し、一酸化炭素10気圧雰囲気下で100度で2時間処理することにより、触媒を調製した。ここに、エチレンオキシドと一酸化炭素の混合物を、表1に示す条件で流通させた。得られた生成物は高速液体クロマトグラフィー及びガスクロマトグラフィーによって分析した。その結果を表1に併せて示す。

### 【0023】

【表1】

実施例 No.	CO/E <sup>*</sup> 比	反応温度 (°C)	反応圧 (atm)	接触時間 (S)	転化率** (%)	選択率(%)	
						2-オキセタノン	その他
4	1	80	30	0.2	25	100	0
5	10	60	10	3.0	35	100	0
6	20	40	1	8.0	32	100	0
7	40	30	1	8.0	22	100	0
8	10	100	40	0.2	17	98	2
9	10	60	10	0.05	11	100	0
10	10	60	10	20.0	31	93	7
11	0.5	60	10	3.0	6	100	0
12	100	60	10	3.0	8	83	17
13	10	10	10	3.0	5	100	-
14	10	150	10	3.0	27	21	78
15	10	60	70	3.0	5	100	0
16	10	60	10	0.001	7	100	0
17	10	80	10	100.0	36	49	51

\* ...エチレンオキシドに対する一酸化炭素のモル比

\*\*...エチレンオキシドの転化率

**THIS PAGE BLANK (USPTO)**



JP 09-169753 A

(11) Publication number : 09-169753 (51) Int.Cl. C07D305/12  
(43) Date of publication of application : 30.06.1997  
(21) Application number : 07-332967 (71) Applicant : TOKUYAMA CORP  
(22) Date of filing : 21.12.1995 (72) Inventor : HATTORI NORIKAZU  
NISHIDA HARUO

(54) PRODUCTION OF COMPOUND OF 2-OXETANONES

(57) Abstract:

PROBLEM TO BE SOLVED: To suppress the formation of by-products and stably obtain a 2- oxetanones compound useful as a raw material for chemicals, polymers, especially a biodegradable polypropiolactone, etc., in high selectivity by passing an oxirane compound and carbon monoxide through a specific catalyst, bringing the compound and carbon monoxide into contact with the catalyst to react the compound with carbon monoxide.

SOLUTION: (B) A compound of formula I (R1 and R4 are each H or a hydrocarbon group) (e.g. ethylene oxide, propylene oxide or styrene oxide), etc., and (C) carbon monoxide are passed through (A) a cobalt-based catalyst (e.g. a catalyst obtained by carrying dicobalt octacarbonyl, cobalt nitrate or cobalt acetate onto a support such as silica gel, alumina or zeolite and heat-treating the material under atmosphere such as hydrogen, nitrogen or carbon monoxide) and brought into contact with the catalyst to react the compound of formula I with carbon monoxide and obtain the objective compound such as a compound of formula II or formula III (e.g. 2-oxetane, 4-methyl-2-oxetane or 4 phenyl-2 oxetanone).

**Disclaimer**

This is a machine translation performed by NCIPPI (<http://www.ipdl.ncipi.go.jp>) and received and compiled with PatBot (<http://www.patbot.de>). PatBot can't make any guarantees that this translation is received and displayed completely!

**Notices from NCIPPI**

Copyright (C) JPO, NCIPPI

The JPO and NCIPPI are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. \*\*\*\* shows the word which can not be translated.
3. In the drawings, any words are not translated.

---

CLAIMS

---

[Claim(s)]

[Claim 1]The manufacture approach of 2-OKISETANON compound characterized by contacting an oxirane compound and a carbon monoxide for a cobalt system catalyst under circulation, and making them react to it.

---

DETAILED DESCRIPTION

---

[Detailed Description of the Invention]

[0001]

[Field of the Invention]This invention relates to the manufacture approach of 2-OKISETANON by the circulation type reaction which used the cobalt system catalyst.

[0002]

[Description of the Prior Art]The manufacture approach of 2-OKISETANON compound known best makes ketenes and aldehydes react to the bottom of existence of the Friedel crafts system catalyst. However, it was difficult for ketenes and the aldehydes themselves to obtain what has high purity in many cases, and since moreover both reactivity was high, the problem that the by-product of a large quantity and varieties mixed was in obtained 2-OKISETANON compound. As a by-product, carboxylic acids and those acid anhydrides, such as an acetic acid, an acrylic acid, and 3-hydroxypropionic acid, are main, and these show remarkable polymerization inhibitory action, when carrying out the polymerization of the 2-OKISETANON compound.

[0003]The oligomer of 2-OKISETANON has been obtained in British JP,1020575,B as a principal component, and it is described to it by by performing a batch type reaction for ethyleneoxide and a carbon monoxide with 100 to 300 atmospheric pressure 100 degrees to the bottom of dicobaltooctacarbonyl catalyst existence that 2-OKISETANON also exists in this product.

[0004]Moreover, the technique of obtaining 2-OKISETANON compound by high yield is shown to JP,6-65223,A by by carbonylating an oxirane compound with a carbon monoxide at a batch type reaction using the catalyst system which consists of a source of cobalt, and a hydroxy permutation pyridine compound. However, in order that the hydroxy permutation pyridine compound in the used catalyst system may act as a polymerization initiator of generated 2-OKISETANON compound, carrying out the polymerization of the generated 2-OKISETANON compound immediately with generation is specified in the specification. Therefore, as long as it carries out at a homogeneous system liquid phase batch type reaction in this catalyst system, it is impossible to isolate, before carrying out the polymerization of the 2-OKISETANON compound.

[0005]

[Problem(s) to be Solved by the Invention]This invention offers the manufacture approach that it is in the condition which hardly contains a by-product, and 2-OKISETANON compound can be isolated alternatively.

[0006]

[Means for Solving the Problem]As a result of repeating research wholeheartedly, when this invention persons adopted the flow method and contact time with a catalyst was shortened, they find out that 2-OKISETANON compound can be isolated in the condition that a by-product is hardly included, and came to complete this invention. That is, this invention is the manufacture approach of 2-OKISETANON compound characterized by contacting an oxirane compound and a carbon monoxide for a cobalt system catalyst under circulation, and making them react to it.

[0007]This invention is characterized by making the catalytic reaction shown by

the following formula under circulation perform. By carrying out like this, it can be promptly desorbed from a catalyst bed from 2-OKISETANON compound generated on the catalytic activity point, and 2-OKISETANON compound can be isolated as the result. Moreover, since side reaction is also suppressed, an impurity decreases extremely in 2-OKISETANON compound obtained.

[0008]

[Formula 1]

[0009]

[Embodiment of the Invention] If the oxirane compound in this invention is a compound which contains at least one three membered ring ether structure in the structure, it will not be restricted especially. If the oxirane compound used preferably is illustrated, ethyleneoxide, propylene oxide, isobutene oxide, 2-butene oxide, styrene oxide, 1, 2-epoxy hexane, 1, 2-epoxy octane, cyclohexene oxide, glycidyl methyl ether, glycidyl methacrylate, epichlorohydrin, etc. will be mentioned. As that in which especially reactivity is excellent also in these, ethyleneoxide, propylene oxide, and styrene oxide are used more preferably.

[0010] The cobalt system catalyst in this invention is not restricted especially if it is the catalyst prepared considering the compound (it is also called the source of cobalt) which comes to contain cobalt as a raw material. As this source of cobalt, organometallic compounds, such as an acetylacetonate complex of an inorganic compound like dicobaltoctacarbonyl, a cobalt nitrate, and a cobalt chloride or cobaltous acetate, or cobalt, etc. are mentioned. Also especially in this, dicobaltoctacarbonyl, a cobalt nitrate, cobaltous acetate, etc. are used suitably. Although it is also possible to use these as a catalyst as they are, since this cobalt system catalyst is a catalyst used for a circulation type reaction, what existing as a solid-state supported with the bottom of a reaction condition by the usual sinking-in method etc. preferably therefore on some support, such as silica gel, an alumina, a zeolite, a silica alumina, a zirconia, or inactive glass, is suitable for it. Furthermore, in what was supported on these sources of cobalt, and support, what performed heat-treatment etc. under various gas ambient atmospheres, such as nitrogen, and hydrogen or a carbon monoxide, is used. In addition, if in charge of preparation of a cobalt system catalyst, in addition to the source of cobalt, it can also be used, being able to mix the compound which can serve as a co-catalyst which raises labile. A hydroxy permutation pyridine system compound is mentioned as a co-catalyst used suitably.

[0011] Although it is not limited, when the balance of an invert ratio and selectivity is taken into consideration, as for especially the cobalt concentration on the cobalt system catalyst in this invention, it is desirable that they are per [ 0.01 ] 1ml of catalysts - 10mmol atomic weight, and it is more desirable that it is 0.1 - 5mmol atomic weight. When cobalt concentration is under 0.01mmol atomic weight per 1ml of catalysts, in order to obtain a high invert ratio, it must be filled up with a catalyst so much, and may be industrially disadvantageous. Moreover, even if it exceeds 10mmol atomic weight for cobalt concentration per 1ml of catalysts, there is little effectiveness by having used cobalt so much.

[0012] Although not limited especially about the embodiment of the manufacture approach of this invention, if a general approach is illustrated, it will be as stating below. That is, the coil filled up with the cobalt system catalyst is warmed to predetermined reaction temperature, the raw material which mixed the carbon monoxide with the oxirane compound at the rate of a constant ratio is supplied there by the predetermined rate of flow, and it is made to react in a

catalyst bed. 2-OKISETANON compound is obtained by removing an unreacted raw material oxirane compound and an unreacted carbon monoxide from the reaction mixture which passed the catalyst bed. As long as there is need, distillation purification of the 2-OKISETANON compound may be carried out after that.

[0013]an oxirane compound is mixed with a carbon monoxide in the manufacture approach of this invention -- having -- a raw material -- a catalyst bed is supplied as a mixture. although an oxirane compound and a carbon monoxide react by the mole ratio 1:1 and 2-OKISETANON compound is generated -- raw material mixing -- it is not necessary to necessarily set the mixing ratio in the inside of the body to 1:1, and the direction of yield which made the carbon monoxide superfluous improves. The carbon monoxide of a desirable mixing ratio is one to 20 times more suitably one to 50 times to an oxirane compound. When less than 1 time, an invert ratio and selectivity become low, and since an oxirane compound is diluted too much when exceeding 50 times, an invert ratio tends to fall. In addition, after catalyst bed passage, it dissociates with a product, if the carbon monoxide and the unreacted oxirane compound for an excess are required, they can be refined, and they can be again used as a reaction raw material.

[0014]In the manufacture approach of this invention, although especially the contact time of a reaction raw material and a catalyst is not limited, if the balance of an invert ratio and selectivity is taken into consideration, the range for 0.01 - 30 seconds is suitable. Furthermore, when contact time is the range for 0.1 - 10 seconds, coincidence is realized and a high invert ratio and high selectivity are especially suitable. Contact time is time amount required in order that a raw material may pass through the inside of a catalyst bed here. For example, a catalyst bed is the volume of Xml, and when raw material mixture is supplied by the rate of flow of Yml per second, contact time is a value expressed as a X/Y second. the important element with which this contact time influences an invert ratio and selectivity -- it is -- a raw material -- it is controllable by the speed of supply of a mixture, the cobalt concentration of a catalyst, and the amount of the catalyst used.

[0015]As for the catalytic reaction in this invention, it is desirable to make it go on on comparatively quiet conditions. Although especially reaction temperature is not limited, 20 - 120 degrees is desirable from the balance of an invert ratio and selectivity, and 40 - 80 degrees is more desirable. Atmospheric pressure - 50 atmospheric pressure of reaction pressure is desirable, and its atmospheric pressure - 30 atmospheric pressure is more desirable. When exceeding 50 atmospheric pressures, it may become disadvantageous in cost on the structure of equipment.

[0016]

[Effect of the Invention]Since 2-OKISETANON compound is extremely rich in reactivity, it is useful as the raw material of various chemicals, and a monomer of a polymer. Especially 2-OKISETANON is very important as a raw material monomer of the poly propiolactone which is a biodegradable plastic.

[0017]By this invention, 2-OKISETANON compound can be stably isolated with high selectivity.

[0018]

[Example]Although an example explains this invention to a detail further, this invention is not limited to these examples.

[0019]The catalyst was prepared by filling up the coil made from stainless steel with what supported example 1 dicobaltoctacarbonyl 1g to 7g (5ml) of inactive glass particles of the particle size of 0.8mm, and surface area of 0.65cm<sup>2</sup>/g (cobalt concentration 1.2mmol atomic weight / ml), and processing at 100 degrees under a carbon monoxide 10 atmospheric-pressure ambient atmosphere for 2 hours. The raw material which mixed ethyleneoxide and a carbon monoxide by the ratio of 1:10 here was circulated. 60 degrees, reaction pressure was performed with ten atmospheric pressures, and reaction temperature performed contact time in 1.5 seconds. High performance chromatography and a gas chromatography analyzed the

obtained product. Consequently, everything but a raw material of the reaction mixture out of which the invert ratio to ethyleneoxide came from the coil 30% is only 2-OKISETANON, and other by-products were not detected.

[0020]The catalyst was prepared by filling up the coil made from stainless steel with what supported example 2 dicobaltoctacarbonyl 1g to 3.5g (6.5ml) of silica gel particles of the particle size of 75-500 micrometers, and surface area of 500m<sup>2</sup>/g (cobalt concentration 0.9mmol atomic weight / ml), and processing at 100 degrees under a carbon monoxide 10 atmospheric-pressure ambient atmosphere for 2 hours. The raw material which mixed propylene oxide and a carbon monoxide by the ratio of 1:10 here was circulated. 60 degrees, reaction pressure was performed with ten atmospheric pressures, and reaction temperature performed contact time in 0.5 seconds. High performance chromatography and a gas chromatography analyzed the obtained product. Consequently, the selectivity of 4-methyl-2-OKISETANON in the reaction mixture out of which the invert ratio to propylene oxide came from the coil 25% is 100%, and other by-products were not detected.

[0021]The catalyst was prepared by filling up the coil made from stainless steel with what supported example triacetic acid cobalt 1g to 3.5g (5.2ml) of activated-alumina particles of the particle size of 100-300 micrometers, and surface area of 200m<sup>2</sup>/g (cobalt concentration 1.1mmol atomic weight / ml), and processing at 100 degrees under a carbon monoxide 10 atmospheric-pressure ambient atmosphere for 2 hours. The raw material which mixed styrene oxide and a carbon monoxide by the ratio of 1:10 here was circulated. 60 degrees, reaction pressure was performed with ten atmospheric pressures, and reaction temperature performed contact time in 8 seconds. High performance chromatography and a gas chromatography analyzed the obtained product. Consequently, the selectivity of 4-phenyl-2-OKISETANON in the reaction mixture out of which the invert ratio to styrene oxide came from the coil 21% is 100%, and other by-products were not detected.

[0022]The catalyst was prepared by filling up the coil made from stainless steel with what supported example 4 - 17 dicobaltoctacarbonyl 1g to 7g (5ml) of inactive glass particles of the particle size of 0.8mm, and surface area of 0.65cm<sup>2</sup>/g (cobalt concentration 1.2mmol atomic weight / ml), and processing at 100 degrees under a carbon monoxide 10 atmospheric-pressure ambient atmosphere for 2 hours. It was made to circulate here on the conditions which show the mixture of ethyleneoxide and a carbon monoxide in Table 1. High performance chromatography and a gas chromatography analyzed the obtained product. The result is collectively shown in Table 1.

[0023]

[Table 1]



BEST AVAILABLE COPY

**THIS PAGE BLANK (USPTO)**